

Technical specification

Polyether D 35150

Description Can be used for acoustic purposes in automotive and other industries.

Properties	Unit	Value	Test method
Density	kg/m ³	31-34	ISO 845
Hardness (ILD 40%)	N	150 +/- 15%	ISO 2439 B
Tensile strength	kPa	130	ISO 1798
Elongation	%	240	ISO 1798
Compression set 50 %	%		
Flammability	mm/min	SE eller < 75	FMVSS 302
Fogging reflection	%	>90	Saab STD 1082
Standard colour		Grey	
Tear strength	N/cm	>5	ASTDM D 3574 F
Formaldehyde content	mg/kg		STD 1027.2749
TVOC	µg C/g		STD 1027.2749

This specification is given by our best knowledge and might be submitted to changes.