Technical specification

Isoseal LP F 18 E

Description Can be used as packaging, acoustical absorption, flame lamination, padding, sealing, thermal insulation etcetera.

Properties	Unit	Value	Test method
Density (net)	kg/m³	39 – 44	ISO 845
Hardness (CDH 40%)	kPa	6.0 – 9.0	ISO 3386
Tensile strength	kPa	> = 140	ISO 1798
Elongation	%	150	ISO 1798
Compression set	%	> = 14	ISO 1856/A
Flammability	mm/min	> 100	MVSS 302
Fogging reflection	mg	-	
Standard colour		Grey	
Tear strength	N/cm	-	
Formaldehyde content	mg/kg	-	
TVOC	µg C/g	-	

This specification is given by our best knowledge and might be submitted to changes.

Sundquist Components AB
Phone: +46 40 180075 • Fax: +46 40 294025
info@sundquistcomp.se • www.sundquistcomp.se