

Technical specification

Polyether 20 kg T 23120

Description Sealing properties. Can be used in mattress and as wrapping.

Properties	Unit	Value	Test method
Density	kg/m ³	20-22	ISO 845
Hardness (ILD 40%)	N	120 + - 15%	ISO 2439 B
Tensile strength	kPa	130	ISO 1798
Elongation	%	200	ISO 1798
Compression set	%	-	
Flammability	mm/min	-	
Fogging	%	-	
Standard colour		White	
Tear strength	N/cm	5	ASTM D 3574 F
Formaldehyde content	mg/kg	-	
TVOC	µg C/g	-	
Temperature use			
°C min		- 40	
°C max		+ 120	

This specification is given by our best knowledge and might be submitted to changes.