

Technical specification

Polyether Foam – RF 26030

Description Can be used for acoustic purposes in automotive and other industries.

Properties	Unit	Value	Test method
Density	kg/m ³	26	ISO 845
Hardness (40%)	N	120	ISO 2439
Tensile strength	kPa	100	ISO 1798
Elongation	%	200	ISO 1798
Compression set	%	< 4	ISO 1856
Flammability	mm/min	< 100	FMVSS 302
Fogging	%	60.3	FLTM BO 116-03
Standard colour		-	
Tear strength	N/m	505	ISO 8067
Formaldehyde content	mg/kg	-	
TVOC	µg C/g	-	

This specification is given by our best knowledge and might be submitted to changes.