Technical specification

Polyester S 334 D

Description Can be used as packaging, acoustical absorption, flame lamination, padding, sealing, thermal insulation etcetera.

Properties	Unit	Value	Test method
Density (net)	kg/m³	28-32	ISO 845
Hardness (CDH	kPa	3.6 – 5.4	ISO 3386
Tensile strength	kPa	140	ISO 1798
Elongation	%	190	ISO 1798
Compression set	%	-	
Flammability	mm/min	< 100	MVSS 302
Fogging	%	-	
Standard colour		black	
Tear strength	N/m	-	
Formaldehyde content	mg/kg	-	
TVOC	µg C/g	-	

This specification is given by our best knowledge and might be submitted to changes.

Sundquist Components AB
Phone: +46 40 180075 • Fax: +46 40 294025
info@sundquistcomp.se • www.sundquistcomp.se