

Technical specification

Polyethylene foam LF301DX

Description Can be used for acoustic purposes in automotive and other industries.

Properties	Unit	Value	Test method
Density	kg/m ³	26-29	ISO 845
Tensile Strength	Kpa	>110	ISO 1798
Elongation at break	%	>180	ISO 1798
Tear strength	N/cm	>5	ASTDM D 3574 F
Flammability	mm/min	<75	FMVSS 302

This specification is given by our best knowledge and might be submitted to changes.