

Technical specification

Bulpren S 28280

Description

Polyester foam with fully open cells. Reticulated foams from polyurethane based on polyester polyol. Excellent for air filtration. Can be used in air-conditioning and ventilation systems and in the automotive industry. Applications are dust-, air-, fluid-, fuel filters and more. Successfully stop tiny and natural air emissions and heavy, harmful chemical compounds.

Properties	Unit	Value	Test method
Net Density	kg/m ³	23-27	ISO 845
Compression Resistance at 40%	kPa	2.0-4.0	ISO 3386/1
Tensile strength	KPa	100	ISO 1798
Ultimate Elognation	%	250	ISO 1798
Visiocell (Cell diameter)	Micron	2300-3300	Recticel SS/T.013.4

This specification is given by our best knowledge and might be submitted to changes.